

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):


- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

We claim:

1. In a hydrogel formed from the polymerization product of a monomer mixture comprising silicone prepolymers having the generic formula:



wherein;

A is an activated unsaturated radical;

A' is either an activated unsaturated radical or an alkyl group;


R₁-R₁₀ are independently an alkyl, fluoroalkyl, alcohol, ether, or fluoroether group having 1-10 carbons, or an aromatic group having 6-18 carbons;

m, n, and p are independently 0 to 200, m+n+p being from about 15 to 200;

a is 1 to 10; and


b is 0 to 10,

wherein the silicone prepolymer is prepared by the reaction of a cyclic siloxane (D) and a dimethacrylate disiloxane (M₂) in the presence of a catalyst, the improvement comprising adding at least one disiloxane (T₂) having the formula:



wherein R_{11} - R_{16} are independently an alkyl group having 1-5 carbons,
to the reaction mixture used to form the silicone prepolymer.


2. The method of claim 1, wherein crosslinking density of said hydrogel decreases as the amount of said T_2 increases.
3. The method of claim 1, wherein dimethacrylate disiloxane (M_2) is represented by the formula:



4. The method of claim 1, wherein $m+n+p$ of said polysiloxane prepolymer is within a range of about 25 to 50.
5. The method of claim 4, wherein $m+n+p$ of said polysiloxane prepolymer is about 25.

6. The method of claim 1, wherein said polysiloxane prepolymer is endcapped with 1 to 70 mole % trimethylsilyl.
7. The method of claim 6, wherein said prepolymer is endcapped within the range of 25 to 50 mole % trimethylsilyl.
8. The method of claim 7, wherein said prepolymer is endcapped within the range of 40 to 50 mole % trimethylsilyl.
9. The method of claim 1, wherein $m+n+p$ of said polysiloxane prepolymer is about 25 and endcapped with about 50 mole % trimethylsilyl.
10. The method of claim 1, wherein D is octamethylcyclotetrasiloxane.
11. The method of claim 1, wherein D is 1,1,3,3-tetramethyl-1,3-disila-2-oxacyclopentane.
12. The method of claim 1, wherein D is hexamethylcyclotrisiloxane.
13. The method of claim 1, wherein said catalyst is trifluoromethane sulfonic acid.
14. The method of claim 1, wherein T_2 is hexamethyl disiloxane.
15. The method of claim 1, wherein said monomer mixture further comprises a hydrophilic monomer.
16. The method of claim 15, wherein said hydrophilic monomer is an acrylic-containing monomer.
17. The method of claim 16, wherein said hydrophilic monomer is N,N-dimethyl acrylamide.
18. The method of claim 15, wherein said hydrophilic monomer is a vinyl-containing monomer.
19. The method of claim 18, wherein said hydrophilic monomer is N-vinyl pyrrolidone.

20. The method of claim 15, still further comprising a monofunctional, ethylenically unsaturated silicone-containing monomer.
21. The method of claim 20, wherein said monofunctional, ethylenically unsaturated silicone-containing monomer is represented by the formula:



wherein:


X denotes -COO-, -CONR⁴-, -OCOO-, or -OCONR⁴- where each where R⁴ is independently H or lower alkyl; R³ denotes hydrogen or methyl; h is 1 to 10; and each R² independently denotes a lower alkyl radical, a phenyl radical or a radical of the formula

$$-\text{Si}(\text{R}^5)_3$$

wherein each R⁵ is independently a lower alkyl radical or a phenyl radical.

22. The method of claim 1, wherein said monomer mixture further comprises a UV initiator.
23. The method of claim 22, wherein said UV initiator is Darocur 1173.
24. The method of claim 1, wherein said monomer mixture further comprises a diluent.
25. The method of claim 24, wherein said diluent is hexanol.
26. A silicone-containing, hydrogel formed from the polymerization product of a monomer mixture comprising:

(a) polysiloxane prepolymers represented by the formula:



wherein;

A is an activated unsaturated radical;

A' is either an activated unsaturated radical or an alkyl group;


R₁-R₁₀ are independently an alkyl, fluoroalkyl, alcohol, ether, or fluoroether group having 1-10 carbons, or an aromatic group having 6-18 carbons;

m, n, and p are independently 0 to 200, m+n+p being from about 23 to 200;

a is 1 to 10; and

b is 0 to 10

wherein the silicone prepolymer is prepared by the reaction of dimethacrylate disiloxane (M₂) and cyclic siloxane (D) in the presence of a catalyst, the improvement comprising adding at least one disiloxane (T₂) having the formula:



wherein R_{11} - R_{16} are independently an alkyl group having 1-5 carbons,


to the reaction mixture used to form the silicone prepolymer;

(b) a hydrophilic monomer; and

(c) a monofunctional, ethylenically unsaturated silicone-containing monomer.

27. The hydrogel of claim 26, wherein $m+n+p$ of said polysiloxane prepolymer is within the range of 25 to 50.
28. The hydrogel of claim 27, wherein $m+n+p$ of said polysiloxane prepolymer is about 25.
29. The hydrogel of claim 26, wherein said polysiloxane prepolymer is endcapped within the range of 1 to 70 mole % trimethylsilyl.
30. The hydrogel of claim 29, wherein said prepolymer is endcapped within the range of 25 to 50 mole % trimethylsilyl.
31. The hydrogel of claim 30, wherein said prepolymer is endcapped within the range of 40 to 50 mole % trimethylsilyl.
32. The hydrogel of claim 26, wherein $m+n+p$ of said polysiloxane prepolymer is about 25 and endcapped with about 50 mole % trimethylsilyl.
33. The hydrogel of claim 26, wherein T_2 is hexamethyl disiloxane.
34. The hydrogel of claim 26, wherein said hydrophilic monomer is an acrylic-containing monomer.
35. The hydrogel of claim 34, wherein said hydrophilic monomer is N,N-dimethyl acrylamide.
36. The hydrogel of claim 26, wherein said hydrophilic monomer is a vinyl-containing monomer.

37. The hydrogel of claim 36, wherein said hydrophilic monomer is N-vinyl pyrrolidone.
38. The hydrogel of claim 26, wherein said monofunctional, ethylenically unsaturated silicone-containing monomer is represented by the formula:



wherein:

X denotes -COO-, -CONR⁴-, -OCOO-, or -OCONR⁴- where each where R⁴ is independently H or lower alkyl; R³ denotes hydrogen or methyl; h is 1 to 10; and each R² independently denotes a lower alkyl radical, a phenyl radical or a radical of the formula



wherein each R⁵ is independently a lower alkyl radical or a phenyl radical.

39. The hydrogel of claim 26, wherein the monomer mixture further comprises a UV initiator.
40. The hydrogel of claim 39, wherein said UV initiator is Darocur 1173.
41. The hydrogel of claim 26, wherein the monomer mixture further comprises a diluent.
42. The hydrogel of claim 41, wherein the diluent is hexanol.
43. A contact lens comprising the hydrogel of claim 26.
44. An intraocular lens comprising the hydrogel of claim 26.